

REFRACTION

Angle of divergence	angle of illumination			
	5°	20°	30°	40°
12'	504 Cd/Lux mq.	470 Cd/Lux mq.	370 Cd/Lux mq.	160 Cd/Lux mq.
20'	348 Cd/Lux mq.	346 Cd/Lux mq.	295 Cd/Lux mq.	150 Cd/Lux mq.
1°	30 Cd/Lux mq.	28 Cd/Lux mq.	24 Cd/Lux mq.	35 Cd/Lux mq.
1°30'	15 Cd/Lux mq.	14 Cd/Lux mq.	13 Cd/Lux mq.	7 Cd/Lux mq.

Values given refer to the non transferred product : should transferring not be carried out properly, changes might occur. Variations might depend also on the type of support where the material is transferred onto.